

		PPC Group Services (Pty) Ltd Chain Avenue, Montague Gardens Tel: (021) 550 2174/2197 Facsimile: (021) 550 2188				Customer	Cape Stone		
						Address	Hermanus		
						Tel:			
						Email:	clinton@capestone.co.za chris@capestone.co.za		
Cubes were tested in accordance with SANS 5863:2006 on compression machines MGL 102 or MGL 104. Cubes were weighed on scale MGL 006.									
These results apply only to the samples tested - refer to SABS 0100 - 2:1992 (as amended 1994) for guidance on the interpretation of cube test results.									
This summary sheet is used in lieu of report sheet MGWS 004 at client's request.						Tests were performed under the supervision of Antofogasta Mokoena			
PPC Job Reference	Client's cube reference	Date cast	Date tested	Age at test (days)	Size (mm)	Mass (kg)	Load at failure (kN)	Stress (MPa)	Remarks
CS 36	C11	09-Apr-26	07-May-26	28	100	2,29	373	37,5	
CS 36	C11	09-Apr-26	07-May-26	28	100	2,28	372	37,0	
CS 36	C11	09-Apr-26	07-May-26	28	100	2,26	358	36,0	

Compiled by A.Mokoena 